




Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) **EP 1 170 310 A2**

(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:
09.01.2002 Bulletin 2002/02

(51) Int Cl.7: **C08F 212/14, C08F 8/36,
C08J 3/24, C08J 5/22,
H01M 8/10**

(21) Application number: 01305699.9

(22) Date of filing: 29.06.2001

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE TR**
Designated Extension States:
AL LT LV MK RO SI

(72) Inventor: **Kim, Hae-kyoung.**
c/o Samsung Advanced Ins. of Tech
Yongin-city, Kyungki-do (KR)


(30) Priority: 30.06.2000 KR 2000037394

(74) Representative: **Kyle, Diana**
Elkington and Fife Prospect House 8 Pembroke
Road
Sevenoaks, Kent TN13 1XR (GB)

(71) Applicant: **SAMSUNG ELECTRONICS CO. LTD.**
Suwon-city, Kyungki-do (KR)

(54) **Partially fluorinated copolymer based on trifluorostyrene and substituted vinyl compound and ionic conductive polymer membrane formed therefrom**

(57) A trifluorostyrene and substituted vinyl compound based partially fluorinated copolymer, an ionic conductive polymer membrane including the same, and a fuel cell adopting the ionic conductive polymer membrane are provided. The partially fluorinated copolymer has formula (1):



where each of R_1 , R_2 and R_3 is F, H or CH_3 ; X is a hydroxy group or a trifluoromethyl group; m is an integer greater than zero; n is an integer greater than zero; and p, q and r are zero or integers greater than zero. The copolymer having formula (1) includes trifluorostyrene units and substituted vinyl compound units, which may be partially crosslinked. Ionic conductive polymer membranes can be manufactured using the copolymer at low cost, with excellent mechanical properties. When a partially crosslinked copolymer is used, the degree of swelling of the resulting polymer membrane and fuel crossover can be reduced. The efficiency of fuel cells can be improved by adopting the ionic conductive polymer membrane.

EP 1 170 310 A2

BEST AVAILABLE COPY

Description

[0001] The present invention relates to a trifluorostyrene and substituted vinyl compound based partially fluorinated copolymer, and an ionic conductive polymer membrane formed of the same, and more particularly, a partially fluorinated copolymer with trifluorostyrene units and substituted vinyl compound units, an ionic conductive polymer membrane formed of the copolymer, which has excellent mechanical properties and a low degree of swelling caused by water absorption, and a fuel cell having the ionic conductive polymer membrane.

[0002] Recently, with the advance of portable electronic devices and wireless communications devices, the need for high performance fuel cells for these portable devices is extensively increasing. For the improved efficiency of fuel cells, a polymer membrane which ensures a high ionic conductivity and reduces cross-over of fuel, particularly of methanol, is needed.

[0003] Fuel cells are novel power generating systems which convert the energy generated by the electrochemical reaction of a fuel and an oxidizing gas to electrical energy for use. Fuel cells are classified into, for example, fuel cells with molten carbonate salt electrolyte operable at a high temperature of 500-700°C, fuel cells with phosphoric acid electrolyte operable around 200°C, fuel cells with alkali electrolyte operable in the wide range of temperatures from room temperature to 100°C or less, fuel cells with a proton exchange membrane as the electrolyte, and fuel cells with solid electrolyte operable at a high temperature of 600-1000°C.

[0004] The polymer electrolyte fuel cell includes a proton exchange membrane fuel cell (PEMFC) using hydrogen gas as fuel, and a direct methanol fuel cell (DMFC) which uses liquid methanol from the anode as direct fuel.

[0005] The proton exchange membrane fuel cell (PEMFC), a future clean energy source emerging as a substitute for fossil energy, has high output density and energy conversion efficiency. Also, the PEMFC is workable at room temperature and is easy to seal and miniaturize, so that it can be extensively used in the fields of pollution-free vehicles, household power generating systems, mobile telecommunications, portable power generating systems, and medical, military and space equipment.

[0006] The PEMFC is a power generator for producing direct current through the electrochemical reaction of hydrogen and oxygen. The basic structure of such a cell is shown in FIG. 1. Referring to FIG. 1, the PEMFC has a proton exchange membrane 11 interposed between the anode and the cathode.

[0007] The proton exchange membrane 11 is formed of a solid polymer electrolyte with a thickness of 20-200 μm . The anode and cathode includes support layers 14 and 15 for supplying reaction gas, and catalytic layers 12 and 13 in which oxidation/reduction of the reaction gas occurs, which collectively form a "gas diffusion electrode." In FIG. 1, reference numeral 16 represents a current collector.

[0008] In the PEMFC having the above structure, with application of hydrogen gas as a reaction gas, hydrogen molecules are decomposed into hydrogen ions and electrons by oxidation reaction in the anode. The produced hydrogen ions reach the cathode through the proton exchange membrane 11.

[0009] Meanwhile, in the cathode, oxygen molecules take electrons from the anode through the membrane and are reduced to oxygen ions by reduction. The produced oxygen ions react with hydrogen ions from the anode and produce water molecules.

[0010] As shown in FIG. 1, in the PEMFC, the catalytic layers 12 and 13 of the gas diffusion electrode are formed over the support layers 14 and 15, respectively. The support layers 14 and 15 are formed of carbon cloth or carbon paper. The surface of the support layers 14 and 15 are treated so as to allow easy passing of reaction gas, water to the proton ion exchange membrane 11, and water obtained as the reaction product.

[0011] On the other hand, the DMFC has the same structure as that of the PEMFC, but using liquid methanol, instead of hydrogen, as a reaction fuel. As the liquid methanol is supplied to the anode, an oxidation reaction occurs in the presence of a catalyst, so that hydrogen ions, electrons and carbon dioxide are generated. The DMFC has poor cell efficiency compared with the PEMFC because of lower catalytic activities of anodic fuel. However, the use of liquid fuel makes its application to portable electronic devices easier.

[0012] The previously mentioned fuel cells usually employ an ionic conductive polymer membrane as the proton exchange membrane disposed between the anode and the cathode. The ionic conductive polymer membrane as an electrolyte of the fuel cell, serves to transfer hydrogen ions from the anode to the cathode, and prevents the fuels for each of the anode and cathode from mixing with each other. In addition, the ionic conductive polymer membrane is formed of a polymer membrane with sulfonyl group as side chain. Because the polymer membrane contains water, a sulfonic acid group of the polymer electrolyte is dissociated in the water medium so that the sulfonyl group is produced with ionic conductivity.

[0013] The ionic conductive polymer membrane should have the following characteristics: a high ionic conductivity, electrochemical stability, mechanical properties suitable as a membrane, thermal stability at working temperature, easy processing into a thin film for reduced resistance, low cost and low degree of swelling caused by liquid absorption, etc.

[0014] The most widely known ionic conductive polymer membrane has a polytetrafluoroethylene backbone having sulfonyl group as side chains. However, this polymer membrane is of little practical use due to its high manufacturing

cost and complicated manufacturing process. To solve these problems, an ionic conductive polymer membrane formed of polytrifluorostyrene, a partially fluorinated polymer, has been suggested in U.S. Patent Nos. 5,422,411; 5,498,639, 5,602,185; 5,684,192; 5,773,480; and 5,834,523. However, the ionic conductive polymer based on sulfonated polytrifluorostyrene is known to be very brittle and thus has difficulty in practical use. For this reason, to enhance the mechanical strength of the polymer membrane, there has been used a copolymer of trifluorostyrene, and a polymer which is able to be polymerized with trifluorostyrene, for example, a monomer containing fluorine with long side chain, such as heptadecafluoro decyl acrylate, heptadecafluoro decene, hydroxypropyl methacrylate, hydroxybutyl acrylate and hydroxyethyl methacrylate.


[0015] When the ionic conductive polymer membrane is applied to a fuel cell, the polymer membrane absorbs water and serves as a medium which allows hydrogen ions to pass. As the polymer membrane absorbs water, the thickness and the area of the polymer membrane varies by swelling. However, if the degree of the swelling is excessive, due to the difference between the dry state and the full water absorption state, there is a difficulty in fuel cell manufacturing with the polymer membrane.

[0016] To solve the above problems, it is a first objective of the present invention to provide a copolymer based on trifluorostyrene and substituted vinyl compound.

[0017] A second objective of the present invention is to provide an ionic conductive polymer membrane formed of the copolymer, which has a low degree of swelling caused by water absorption and excellent mechanical properties.


[0018] A third objective of the present invention is to provide a fuel cell with improved efficiency, which employs the ionic conductive polymer membrane.

[0019] Accordingly, to achieve the above objective, there is provided a partially fluorinated copolymer having formula (1) below, comprising trifluorostyrene units and substituted vinyl compound units:




where each of R_1 , R_2 and R_3 is F, H or CH_3 ; X is a hydroxy group or a trifluoromethyl group; m is an integer greater than zero; n is an integer greater than zero; p, q and r are zero or integers greater than zero.

[0020] The second objective of the present invention is achieved by an ionic conductive polymer membrane comprising a partially fluorinated copolymer having formula (1) with trifluorostyrene units and substituted vinyl compound units:



where each of R_1 , R_2 and R_3 is F, H or CH_3 ; X is a hydroxy group or a trifluoromethyl group; m is an integer greater than zero; n is an integer greater than zero; p, q and r are zero or integers greater than zero.

[0021] The third objective of the present invention is achieved by a fuel cell adopting an ionic conductive layer including a partially fluorinated copolymer having formula (1) with trifluorostyrene units and substituted vinyl compound units:



where each of R_1 , R_2 and R_3 is F, H or CH_3 ; X is a hydroxy group or a trifluoromethyl group; m is an integer greater than zero; n is an integer greater than zero; p, q and r are zero or integers greater than zero.

[0022] The above objectives and advantages of the present invention will become more apparent by describing in detail preferred embodiments thereof with reference to the attached drawings in which:

FIG. 1 illustrates the structure of a conventional fuel cell adopting a proton exchange membrane;

FIG. 2 is a graph illustrating the variation in ionic conductivity of the inventive ionic conductive polymer membrane of Synthesis Example 1 with respect to temperature;

FIG. 3 is a graph illustrating the variation in cell potential of the proton exchange membrane fuel cell (PEMFC) manufactured in Example 1 with respect to current density; and

FIG. 4 is a graph illustrating the variation in cell potential of the inventive direct methanol fuel cell (DMFC) manufactured in Example 2 with respect to current density.

[0023] A partially fluorinated copolymer having formula (1) above according to the present invention is derived by polymerizing a trifluorostyrene monomer and a substituted vinyl compound monomer, and sulfonating the polymerized product. The trifluorostyrene monomer may include, for example, α,β,β -trifluorostyrene, heptadecafluoro decyl methacrylate, heptadecafluoro decene and heptadecafluoro decyl acrylate.




[0024] The polymerization reaction of the trifluorostyrene monomer and the substituted vinyl compound monomer will be described in greater detail. In the present invention, the polymerization reaction is performed by an emulsion polymerization method. A polymerization initiator, for example, potassium persulfate, can be added for the polymerization. Dodecylamine hydrochloride or sodium stearate (soap) can be used as an emulsifier.


[0025] When the polymerization of the trifluorostyrene monomer and the substituted vinyl compound monomer is completed, an emulsifier used in the emulsion polymerization is removed and the copolymer is subjected to sulfonation with a chlorosulfonic acid. The degree of sulfonation can be varied by adjusting the amount of a sulfonation agent such as chlorosulfonic acid. After the sulfonation is completed, an ionic conductive polymer membrane for fuel cells is obtained by casting a solution containing the resultant sulfonated copolymer or hot pressing the resultant sulfonated copolymer.

[0026] In formula (1) above, preferably, m is an integer from 1 to 50, n is an integer from 1 to 50, p is zero or an integer from 1 to 12, and q is zero or an integer from 1 to 12.

[0027] Preferably, the partially fluorinated copolymer having formula (1) above has a weight average molecular weight of 30,000-500,000. If the weight average molecular weight of the partially fluorinated copolymer is less than 30,000, formation of a film is difficult. If the weight average molecular weight of the partially fluorinated copolymer exceeds 500,000, unfavorably its solubility in organic solvent is poor.

[0028] Preferably, the partially fluorinated copolymer having formula (1) above is any compound having formula (2) through (5):






where m is an integer greater than zero; and n is an integer greater than zero. Preferably, in formula (1) through (5), m is an integer from 1 to 50; and n is an integer from 1 to 50.

[0029] The copolymer having formula (1) above can be partially crosslinked with a crosslinking agent, which is a multi-functional compound having two or more unsaturated groups per molecule. The crosslinking reaction takes place when a mixture of the copolymer having formula (1) and the crosslinking agent is subjected to casting or hot pressing to form a polymer membrane.

[0030] The crosslinking agent may be divinyl benzene, diallyl ether, triallyl ether, diglycidyl ether, ethyleneglycol dimethacrylate, or a mixture of these compounds. When partially crosslinking the copolymer having formula (1) with a crosslinking agent, ionic conductivity slightly decreases and the degree of swelling in the wet state is reduced. Thus, a difference in volumes of the polymer membrane in the dry and wet states is decreased.

[0031] The following compounds are derived when divinyl benzene is used as the crosslinking agent.



where m is an integer greater than zero; n is an integer greater than zero; and p and r are zero or integers greater than zero. Preferably, m is an integer from 1 to 50, n is an integer from 1 to 50, p is zero or an integer from 1 to 12, and q

is zero or an integer from 1 to 12.

[0032] On the other hand, in manufacturing a fuel cell according to the present invention, a catalytic layer is formed over both sides of the ionic conductive polymer membrane formed of the copolymer having formula (1), and bonded with each electrode support layer, so that a membrane and electrode assembly (MEA) is completed. Next, a current collector is attached to both sides of the MEA, thereby resulting in a complete fuel cell.

[0033] The present invention will be described in greater detail by means of the following examples. The following examples are for illustrative purposes and are not intended to limit the scope of the invention.

Synthesis Example 1

[0034] 80 g α,β,β -trifluorostyrene, 15 g heptadecafluoro decyl methacrylate, 600 ml deionized water and 9.5 g dodecylamine hydrochloride were placed into a 4-necked flask equipped with a mechanical stirrer and mixed. During the mixing process, the flask was conditioned in a nitrogen atmosphere. Next, the flask containing the reactants was purged with nitrogen gas for 30 minutes, and was then kept at $55 \pm 1^\circ\text{C}$. A solution obtained by dissolving 0.35 g potassium persulfate in 5 g deionized water was injected into the reaction mixture with a syringe. The mixture was left at $55 \pm 1^\circ\text{C}$ for 72 hours for reaction.

[0035] 30 g sodium chloride and 50 g ice were added to the reaction mixture and filtered in a vacuum to obtain copolymer powder. The resultant copolymer powder was washed with deionized water and then with cold methanol. The washed copolymer powder was dried at room temperature for a day, and dried again in a vacuum oven at room temperature for 5-6 hours.

[0036] 4.78 g of the resultant copolymer was completely dissolved in 300 ml chloroform, and 2 ml chlorosulfonic acid was added to the solution with a syringe. The mixture was reacted at 65°C for 3 hours, and cooled to room temperature. Next, the solvent was decanted from the reaction product. Then, methanol was added to the resultant product and evaporated in a vacuum to remove the remaining solvent, thereby resulting in a sulfonated copolymer having formula (2) above. As for the obtained sulfonated copolymer, m and n of formula (2) were 9 and 2, respectively. The weight average molecular weight of the resultant copolymer was 95,000.

[0037] IR(KBr, cm^{-1}): ν 2900, 1730, 1300, 1100-1400

Synthesis Example 2

[0038] 50 g α,β,β -trifluorostyrene, 10 g heptadecafluoro decyl methacrylate, 400 ml deionized water and 5.0 g dodecylamine hydrochloride were placed into a 4-necked flask equipped with a mechanical stirrer and mixed. During the mixing process, the flask was conditioned in a nitrogen atmosphere. Next, the flask containing the reactants was purged with nitrogen gas for 30 minutes, and was kept at $55 \pm 1^\circ\text{C}$. A solution obtained by dissolving 0.25 g potassium persulfate in 5 g deionized water was injected into the reaction mixture with a syringe. The mixture was left at $55 \pm 1^\circ\text{C}$ for 72 hours for reaction.

[0039] 25 g sodium chloride and 50 g ice were added to the reaction mixture and filtered in a vacuum to obtain copolymer powder. The resultant copolymer powder was washed with deionized water and then with cold methanol. The washed copolymer powder was dried at room temperature for a day, and dried again in a vacuum oven at room temperature for 5-6 hours.

[0040] 6 g of the resultant copolymer was completely dissolved in 300 ml chloroform, and 1.2 ml chlorosulfonic acid was added to the solution with a syringe. The mixture was reacted at 65°C for 3 hours, and cooled to room temperature. Next, the solvent was decanted from the reaction product. Then, methanol was added to the resultant product and evaporated in a vacuum to remove the remaining solvent, thereby resulting in a sulfonated copolymer having formula (3) above. As for the obtained sulfonated copolymer, m and n of formula (3) were 8 and 2, respectively. The weight average molecular weight of the resultant copolymer was 80,700.

[0041] IR(KBr, cm^{-1}): ν 3000, 1730, 1300, 1100-1400

Synthesis Example 3

[0042] 20 g α,β,β -trifluorostyrene, 5 g heptadecafluoro decene, 400 ml deionized water and 2.9 g dodecylamine hydrochloride were placed into a 4-necked flask equipped with a mechanical stirrer and sufficiently mixed. During the mixing process, the flask was conditioned in a nitrogen atmosphere. Next, the flask containing the reactants was purged with nitrogen gas for 30 minutes, and was kept at $55 \pm 1^\circ\text{C}$. While maintaining the temperature of the reaction mixture at the temperature, a solution obtained by dissolving 0.2 g potassium persulfate in 5 g deionized water was injected into the reaction mixture with a syringe. The mixture was left at $55 \pm 1^\circ\text{C}$ for 72 hours for reaction.

[0043] After the reaction was completed, 50 g ice and 25 g sodium chloride were added to the reaction mixture and filtered in a vacuum to obtain copolymer powder. The resultant copolymer powder was washed with deionized water

and then with cold methanol. The washed copolymer powder was dried at room temperature for a day, and dried again in a vacuum oven at room temperature for 5-6 hours.

[0044] 6 g of the resultant copolymer was dissolved in 300 ml chloroform, and 1.2 ml chlorosulfonic acid was dropwise added to the solution with a syringe. The mixture was reacted at 65°C for 3 hours, and cooled to room temperature. Next, the solvent was decanted from the reaction product. Then, methanol was added to the resultant product and evaporated in a vacuum to remove the remaining solvent, thereby resulting in a sulfonated copolymer having formula (4) above. As for the obtained sulfonated copolymer, m and n of formula (4) were 13 and 3, respectively. The weight average molecular weight of the resultant copolymer was 82,500.

[0045] IR(KBr, cm^{-1}): ν 3000, 1300, 1100-1400

Synthesis Example 4

[0046] 90 g α,β,β -trifluorostyrene, 30 g hydroxypropyl methacrylate, 500 ml deionized water and 11.8 g dodecylamine hydrochloride were placed into a 4-necked flask equipped with a mechanical stirrer and sufficiently mixed. During the mixing process, the flask was conditioned in a nitrogen atmosphere.

[0047] Next, the flask containing the reactants was purged with nitrogen gas for 30 minutes, and was kept at $55 \pm 1^\circ\text{C}$. While maintaining the temperature of the reaction mixture at the temperature, a solution obtained by dissolving 0.445 g potassium persulfate in 5 g deionized water was injected into the reaction mixture with a syringe. The mixture was left at $55 \pm 1^\circ\text{C}$ for 72 hours for reaction.

[0048] After the reaction was completed, 30 g sodium chloride and 50 g ice were added to the reaction mixture and filtered in a vacuum to obtain copolymer powder. The resultant copolymer powder was washed with deionized water and then with cold methanol. The washed copolymer powder was dried at room temperature for a day, and dried again in a vacuum oven at room temperature for 5-6 hours.

[0049] 8.5 g of the resultant copolymer was dissolved in 500 ml chloroform, and 1.6 ml chlorosulfonic acid was dropwise added to the solution with a syringe. The mixture was reacted at 68°C for 3 hours, and cooled to room temperature. Next, the solvent was decanted from the reaction product. Then, methanol was added to the resultant product and evaporated in a vacuum to remove the remaining solvent, thereby resulting in a sulfonated copolymer having formula (5) above. As for the obtained sulfonated copolymer, m and n of formula (5) were 15 and 14, respectively. The weight average molecular weight of the resultant copolymer was 93,000.

[0050] IR(KBr, cm^{-1}): ν 3600, 2900-2700, 1730

[0051] Ionic conductive polymer membranes were manufactured by hot pressing the sulfonated copolymers derived in Synthesis Examples 1 to 4 at a temperature of 100°C and a pressure of 23 Mton for 5 minutes. Variations in ionic conductivity of the obtained ionic conductive polymer membranes with respect to temperature were measured.

[0052] FIG. 2 illustrates the ionic conductivity of the ionic conductive polymer membrane formed of the sulfonated copolymer of Synthesis Example 1 with respect to temperature. As shown in FIG. 2, the ionic conductivity of the ionic conductive polymer membrane is 10^{-1} S/cm or more in the range of 30-70°C, which is satisfactory to be used as a proton exchange membrane for fuel cells.

[0053] As for the ionic conductive polymer membranes manufactured using the polymers of Synthesis Examples 2 through 4, the ionic conductive properties show a tendency similar to those of the ionic conductive polymer membrane for Synthesis Example 1.

[0054] IR(KBr, cm^{-1}): ν 3600, 2900-2700, 1730

Synthesis Example 5

[0055] 600 ml deionized water, 11.6 g dodecylamine hydrochloride, and 100 g α,β,β -trifluorostyrene were placed into a 4-necked flask equipped with a mechanical stirrer and sufficiently mixed with the stirrer in a nitrogen atmosphere.

[0056] Next, the flask containing the reactants was purged with nitrogen gas for 30 minutes, and was kept at $55 \pm 1^\circ\text{C}$. After dissolving 0.8 g potassium persulfate in deionized water, the solution was injected into the reaction mixture with a syringe.

[0057] The mixture was left for 48 hours for reaction. After the reaction was completed, 50 g ice and 100 g sodium chloride were added to the reaction mixture and filtered in a vacuum to obtain copolymer powder. The resultant copolymer powder was washed with deionized water and then with cold methanol. The washed copolymer powder was dried at room temperature for a day, and dried again in a vacuum oven at room temperature for 5-6 hours. The resultant copolymer has formula (1) above, where $m = 4$.

Example 1

[0058] An ionic conductive polymer membrane was manufactured by hot pressing the sulfonated copolymer obtained

in Synthesis Example 1 at a temperature of 100°C and a pressure of 23 Mton for 5 minutes.

[0059] A catalytic layer was formed on both sides of the ionic conductive polymer membrane, and bonded with each electrode support layer, so that a membrane and electrode assembly (MEA) was manufactured. A current collector was attached to both sides of the completed MEA, thereby resulting in a complete proton exchange membrane fuel cell (PEMFC).

Example 2

[0060] A PEMFC was manufactured in the same manner as in Example 1, except that the sulfonated copolymer of Synthesis Example 2 was used instead of the sulfonated copolymer of Synthesis Example 1.

Example 3

[0061] An ionic conductive polymer membrane was manufactured by hot pressing the sulfonated copolymer obtained in Synthesis Example 1 at a temperature of 100°C and a pressure of 23 Mton for 5 minutes.


[0062] A catalytic layer was formed on both sides of the ionic conductive polymer membrane, and bonded with each electrode support layer, so that a membrane and electrode assembly (MEA) was manufactured. A current collector was attached to both sides of the completed MEA, thereby resulting in a complete direct methanol fuel cell (DMFC).

[0063] Performance of the fuel cells manufactured in Examples 1 through 3 was evaluated. The results are shown in FIGS. 3 and 4. FIGS. 3 and 4 show variations in cell potential of the PEMFC of Example 1 and the DMFC of Example 3, respectively, with respect to current density. As shown in FIGS. 3 and 4, the PEMFC and DMFC which adopt the ionic conductive layer formed of the copolymer of Synthesis Example 1 have good cell potential characteristic at a temperature of 70-80°C. Here, the cell potential characteristic of the PEMFC and DMFC was measured by measuring a voltage level with application of current while fuel is supplied to the cell. The cell potential characteristic is evaluated as excellent when the voltage level increases with application of a constant current.

[0064] The copolymer having formula (1) according to the present invention includes trifluorostyrene units and substituted vinyl compound units, which may be partially crosslinked. Ionic conductive polymer membranes can be manufactured using the copolymer at low cost, with excellent mechanical properties. When a partially crosslinked copolymer is used, the degree of swelling of the resulting polymer membrane and fuel crossover can be reduced compared with a conventional polymer. The efficiency of fuel cells can be improved by applying the polytrifluorostyrene-based ionic conductive polymer membrane.

Claims


1. A partially fluorinated copolymer having formula (1) below, comprising trifluorostyrene units and substituted vinyl compound units:




where each of R_1 , R_2 and R_3 is F, H or CH_3 ; X is a hydroxy group or a trifluoromethyl group; m is an integer greater than zero; n is an integer greater than zero; and p, q and r are zero or integers greater than zero.

2. The partially fluorinated copolymer of claim 1, wherein, in formula (1), m is an integer from 1 to 50, n is an integer from 1 to 50; p is zero or an integer from 1 to 12; and q is zero or an integer from 1 to 12.


3. The partially fluorinated copolymer of claim 1, wherein the partially fluorinated copolymer is a compound having any formulae (2) to (5):




...(2)



...(3)



...(4)



...(5)

where m is an integer from 1 to 50; and n is zero or an integer from 1 to 50.

4. The partially fluorinated copolymer of any one of claims 1 to 3, wherein the partially fluorinated copolymer having formula (1) has a weight average molecular weight of 30,000-500,000.
5. The partially fluorinated copolymer of any one of claims 1 to 4, wherein the partially fluorinated copolymer is partially crosslinked using a crosslinking agent.
6. The partially fluorinated copolymer of any one of claims 1 to 5, wherein at least one crosslinking agent is divinyl benzene, diallyl ether, triallylether, diglycidyl ether and ethyleneglycol dimethacrylate.
7. An ionic conductive polymer membrane comprising a partially fluorinated copolymer according to any one of claims 1 to 6.
8. A fuel cell adopting an ionic conductive membrane according to claim 7.

FIG. 1 (PRIOR ART)




FIG. 2




FIG. 3







FIG. 4



THIS PAGE BLANK (USPTO)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) **EP 1 170 310 A3**

(12) **EUROPEAN PATENT APPLICATION**

(88) Date of publication A3:
30.01.2002 Bulletin 2002/05

(51) Int Cl.7: **C08F 212/14, C08F 8/36,
C08J 3/24, C08J 5/22,
H01M 8/10**

(43) Date of publication A2:
09.01.2002 Bulletin 2002/02

(21) Application number: 01305699.9

(22) Date of filing: 29.06.2001

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE TR**
Designated Extension States:
AL LT LV MK RO SI

(72) Inventor: **Kim, Hae-kyoung.**
c/o Samsung Advanced Ins. of Tech
Yongin-city, Kyungki-do (KR)


(30) Priority: 30.06.2000 KR 2000037394

(74) Representative: **Kyle, Diana**
Elkington and Fife Prospect House 8 Pembroke
Road
Sevenoaks, Kent TN13 1XR (GB)

(71) Applicant: **SAMSUNG ELECTRONICS CO. LTD.**
Suwon-city, Kyungki-do (KR)

(54) **Partially fluorinated copolymer based on trifluorostyrene and substituted vinyl compound and ionic conductive polymer membrane formed therefrom**

(57) A trifluorostyrene and substituted vinyl compound based partially fluorinated copolymer, an ionic conductive polymer membrane including the same, and a fuel cell adopting the ionic conductive polymer membrane are provided. The partially fluorinated copolymer has formula (1):



...(1)

where each of R_1 , R_2 and R_3 is F, H or CH_3 ; X is a hydroxy group or a trifluoromethyl group; m is an integer greater than zero; n is an integer greater than zero; and p, q and r are zero or integers greater than zero. The copolymer having formula (1) includes trifluorostyrene units and substituted vinyl compound units, which may be partially crosslinked. Ionic conductive polymer membranes can be manufactured using the copolymer at low cost, with excellent mechanical properties. When a partially crosslinked copolymer is used, the degree of swelling of the resulting polymer membrane and fuel crossover can be reduced. The efficiency of fuel cells can be improved by adopting the ionic conductive polymer membrane.



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 01 30 5699

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	WO 96 40798 A (BALLARD POWER SYSTEMS ;STONE CHARLES (CA); STECK ALFRED E (CA)) 19 December 1996 (1996-12-19) * claims 4,13,29-33 * * page 2, line 2 - line 11 * * page 3, line 12 - page 4, line 15 * * page 8, line 27 - page 9, line 14 * * page 9, line 26 - page 11, line 5 * * page 14, line 8 - page 15, line 25 * * page 16, line 3 - line 30 * * page 18, line 2 - line 22; figure 1; examples 5,7 *	1,2,4-8	C08F212/14 C08F8/36 C08J3/24 C08J5/22 H01M8/10
X	US 3 341 366 A (FRANCIS ENOS JOHN ET AL) 12 September 1967 (1967-09-12) * claims 1-11,27,28 *	3-5,7,8	
X	CHEMICAL ABSTRACTS, vol. 97, no. 2, 12 July 1982 (1982-07-12) Columbus, Ohio, US; abstract no. 6870, FREIDLIN, YU. G. ET AL: "Synthesis of a copolymer of.alpha.,.beta.,.beta.-trifluorostyrene with divinylbenzene" XP002184416 * abstract * & PLAST. MASSY (1982), (3), 7-8 , -/--	3-6	TECHNICAL FIELDS SEARCHED (Int.Cl.7) C08F C08J H01M
The present search report has been drawn up for all claims			
Place of search MUNICH		Date of completion of the search 30 November 2001	Examiner Hollender, C
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03.82 (P04C01)



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 01 30 5699

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
A	<p>CHEMICAL ABSTRACTS, vol. 99, no. 16, 17 October 1983 (1983-10-17) Columbus, Ohio, US; abstract no. 123393, FREIDLIN, YU. G. ET AL: "Synthesis and properties of crosslinked copolymers of .alpha., .beta., .beta.-trifluorostyrene and methacrylic acid" XP002184417 * abstract * & PLAST. MASSY (1983), (7), 7-9 ,</p> <p>-----</p>	1-6	
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
The present search report has been drawn up for all claims			
Place of search MUNICH		Date of completion of the search 30 November 2001	Examiner Hollender, C
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPQ FORM 1503 03.82 (P04C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 01 30 5699

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

30-11-2001

Patent document cited in search report		Publication date		Patent family member(s)	Publication date
WO 9640798	A	19-12-1996	AU	5889296 A	30-12-1996
			WO	9640798 A1	19-12-1996
<hr/>					
US 3341366	A	12-09-1967	BE	668486 A	16-12-1965
			CH	463462 A	15-10-1968
			DE	1570681 A1	12-03-1970
			FR	1452148 A	08-12-1966
			GB	1096879 A	29-12-1967
			NL	6510859 A , B	21-02-1966
			SE	337921 B	23-08-1971
			US	3442825 A	06-05-1969
<hr/>					

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☒ FADED TEXT OR DRAWING
- ☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.

THIS PAGE BLANK (USPTO)